

CAPLAST SUPER -M (P)

A HIGH RANGE WATER REDUCING SUPER PLASTICIZER

DESCRIPTION

CAPLAST SUPER -M (P) is a melamine formaldehyde resin based super plasticizing concrete admixture which produces high workability self leveling concrete that requires little or almost no vibration.

CAPLAST SUPER -M (P) CAN be used in powder as well as in liquid form by preparing 25 % solution with water.

FEATURES

CAPLAST SUPER -M (P) has a powerful plasticizing effect on concrete without lowering the surface tension. With water it forms a lubricating film, which reduces the friction between the solid particles. This increases the dispersion that ensures better distribution and thus improved utilization of cement.

STANDARDS

CAPLAST SUPER -M (P) complies with ASTM- C 494 type F.

USES

CAPLAST SUPER -M (P) can be used for obtaining:

- High strength concrete.
- Self leveling, self-compacting concrete.
- Special concrete with :
 - High frost resistance.
 - High abrasion resistance.
 - Low permeability.
 - Excellent pump ability or flowability.

ADVANTAGES

- Increased concrete workability at constant or even improved concrete strengths.
- Improved compacity and hardness.
- High strength mixes with reduced water/cement ratios.

- Due to non-retarding nature of admixture, concrete setting and formwork stripping time is unaffected.
- Flowing concrete simplifies the placing problem. Hence manpower and plant can be effectively used.
- Reduces segregation and bleeding.

TYPICAL PROPERTIES

Appearance:

White granulated material

Bulk Density

500-800 kg/m³

Chloride content:

Nil to BS 5075.

Air entrainment:

Complies with the requirements of ASTM-C 494 clause 12.2.1.

Toxicity:

Non toxic.

Compatibility with cement:

Compatible with all types of Portland, pozzolonic and blast furnace cements.

Compatibility with other admixtures:

Compatible with other Ahlia admixtures, provided they are added separately to the mix.

Shelf life:

At least 24 months if stored in tightly closed containers at normal ambient temperatures.

DIRECTIONS FOR USE

CAPLAST SUPER -M (P) can be used in powder form or as liquid by preparing 25 % solution with water.

CAPLAST SUPER -M (P)

A HIGH RANGE WATER REDUCING SUPER PLASTICIZER

Dosage:

Trials should be carried out to determine the optimum dosages of CAPLAST SUPER -M (P). Or liquid taking into account the relevant mix design, performance requirement and site conditions.

As a general guide

For powder

Dosage Range of 0.36 kg 0.74 kg per 100 kg of cement

For liquid

1.5 liters to 3.0 liters per 100 kg of cement

Dispensing:

Powdered to be dispensed in moist aggregates before addition of sand.

Liquid admixture – best by dispenser into the gauging water or directly with water into the mixer

LIMITATIONS

CAPLAST SUPER -M (P) must not be added directly to dry cement while mixing concrete

OVERDOSING

An overdose of double the recommended dose of CAPLAST SUPER -M (P) can result in slight set retardation. Anyhow the ultimate strength and Properties of the concrete will not be impaired, if properly cured.

SAFETY PRECAUTIONS

CAPLAST SUPER -M (P) is non-toxic and non-flammable. Splashes to eyes and skin should be washed off immediately with abundant water. It is advisable to use goggles and gloves while handling CAPLAST SUPER -M (P).

PACKAGING

CAPLAST SUPER -M (P) is supplied in 10 kg Bags, other packing available by prior arrangement.

STORAGE

Preferably store in sealed conventional containers, protected from extreme weather conditions.

TECHNICAL SERVICE:

Our Technical Service Department is available at any time to advise you in the correct use of this product or any other Ahlia products.

Note : The information presented herein is based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control.

As all Ahlia Technical Data Sheets are updated on a regular basis, it is the user responsibility to collect most recent issue.